



TOTAL PROTECTION

TEK BASE OILS GROUP-II



TEK BASE OILS GROUP II

TEK BASE OILS GROUP II are more refined than Group I and offer better performance in regard to lubricating properties such as volatility, oxidative stability and flash/fire points. They also have better performance in areas such as pour point, cold crank viscosity and extreme pressure wear.

TEK BASE OILS GROUP II is the primary base oil required for most automotive lubricants.

TEK BASE OILS GROUP II son bases más refinadas que el Grupo I, que ofrecen un mejor rendimiento en lo que se refiere a las propiedades lubricantes tales como la volatilidad, estabilidad oxidativa y puntos flash. También tienen un mejor desempeño en áreas como punto de fluidez, viscosidad y desgaste de extrema presión.

TEK BASE OILS es el aceite de base primariamente requerido para la mayoría de los lubricantes para automóviles.

TYPICAL PHYSICAL CHARACTERISTICS

TEST	METHOD	Group II 100	Group II 220	Group II 600
API Gravity	D4052	33.8	31.7	29.5
Viscosity @40 °C , cSt	D445	4.15	6.49	11.9
Viscosity @100 °C , cSt	D445	20.5	42.2	111
Viscosity @100 °F , SUS	Calculated	108	217	579
Viscosity Index	D2270	102	105	96
Dynamic Viscosity				
CCS @ -25 °C, Cp	D5293	1240	-	-
@-20 °C, Cp	D5293	-	2131	-
Sulfur ppm	D2622	<10	<10	<25
Pour Point, °C	D5950	-15	-15	-15
COC Flash Pt, °C,	D92	206	226	262
ASTM Color	D1500	10.5	10.5	11.5
Noack Vol, MM%	D5800	26	11	2
GC, Sim Dist at 700°F %	D6417	16	5	1
Noack Vol, Wt%	D5800	25.3	15.4	
CCR, Wt%	D4530	<0.01	<0.01	0.03
Specific Gravity, 60°F/60°F	D4052	0.8553	0.8667	0.8780

These are typical values subject to stringent industry tolerances.

Consult the Material Safety Data Sheet (MSDS) for safety and handling information.

Estos son valores típicos sujetos a las tolerancias estrictas de la Industria.

Para el manejo del producto consulte la hoja de seguridad (MSDS)



Web: www.tekstarlubricants.com
Product Information: +1-833-434-1321
MSDS Requests: +1-833-434-1321